

HYDROTITE TECHNICAL INFORMATION

CHEMICAL RESISTANCE

Chloroprene rubber has been tested and found compatible with the following materials:

| | |
|------------------------------|-------------------------------|
| acetic acid, 30% | glue |
| aluminium chloride solutions | glycerine |
| aluminium sulphate solutions | n-hexane |
| ammonia, anhydrous | hydraulic oils |
| ammonium chloride solutions | hydrochloric acid, 37% |
| ammonium hydroxide solutions | hydrocyanic acid |
| ammonium sulphate solutions | hydrofluoric acid, 44% |
| amyl alcohol | hydrogen |
| barium hydroxide solutions | hydrogen sulphide |
| borax solutions | isooctane |
| boric acid solutions | isopropyl alcohol |
| butane | lactic acid |
| calcium bisulphite solutions | linseed oil |
| calcium chloride solutions | magnesium chloride solutions |
| calcium hydroxide solutions | magnesium hydroxide solutions |
| carbon dioxide | mercuric chloride solutions |
| carbon monoxide | mercury |
| castor bean oil | methyl alcohol |
| chloroacetic acid | mineral oil |
| citric acid solutions | phosphoric acid, 85% |
| copper chloride solutions | picric acid |
| copper sulphate solutions | sodium hydroxide, 50% |
| cottonseed oil | soya bean oil |
| ethyl alcohol | stannous chloride, 15% |
| ethylene glycol | sulphur dioxide, liquid |
| ferric chloride solutions | tannic acid, 10% |
| fluorosilicic acid | tartaric acid |
| formaldehyde, 40% | triethanolamine |
| freon | tung oil |
| fuel oil | zinc chloride solutions |

